

solvotex cotton premium light S

Technical **I**nformation

➤ **General Information**

- 100 % cotton fabric
- approx. 203 g/m² incl. Inkjet coating
- light linen weave
- white

➤ **Areas of Application**

- printable with solvent, eco solvent as well as with UV – curable inks
- for all kinds of application (indoor)
- especially for displays, banners, exhibitions, presentation, graphic arts, theatre decorations etc.

➤ **Processing & Handling**

- for further handling and storage recommendations please refer to the latest product catalogue or visit our homepage under www.neschen.com
- to avoid fingerprints, protective gloves are recommended to be worn while handling
- to prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured)
- please calculate shrinkage, cotton is a natural fibre and can shrink or expand under the influence of humidity

➤ **Advantages / Special Features**

- highest brilliance in colours
- very good print quality
- good drying time
- high colour resolution is possible
- soft touch
- for more information see the latest Neschen compatibility list (at www.neschen.de)

solvotex cotton premium light S

Technical Information

Technical Data

➤ **Carrier:**

Carrier material:	cotton, coated		
Weight [g/m²]:	approx. 203		
Thickness [µm]:	approx. 322 / approx. 12,5 mil.		
Tear force [N/15mm]:	warp / weft	146 / 151	DIN 53455
Elongation at tear [%]:	warp / weft	12 / 12	
Tear resistance [N/mm²]:	warp / weft	30 / 31	DIN 53455

➤ **Others:**

Shelf life [Months]:	6 - 8
Temperature stability:	n.a.

All tests were performed in accordance with 23/50-2, DIN 50014.

Temperatures in Fahrenheit and thicknesses in mil are given as approximate values. All data are standard values. The information in this specification sheet is based on findings obtained in practice. Because of the high number of factors which can have an effect during handling and application, customer tests will be required. A legally binding guarantee of specific properties is not to be inferred from our specifications. The information given here may be subject to change without notice. Neschen has not prepared MSDSs for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administrations's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the Neschen directions for use, these products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.