

solvotex TCS taft plus 1

Technical Information

➤ **General information**

- 100 % Trevia CS (Polyester with M1 fire classification)
- approx. 90 g/ m² incl. Inkjet coating
- very light linen weave
- white

➤ **Areas of application**

- printable with solvent as well as with UV-curable inks
- for all kinds of application (indoor and outdoor)
- especially for displays, banners, exhibitions, presentation, graphic arts, theatre decorations etc.

➤ **Processing & Handling**

- for further handling and storage recommendations please refer to the latest product catalogue or visit our homepage under www.neschen.com
- to avoid fingerprints, protective gloves are recommended to be worn while handling
- to prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured)
- expected outdoor durability up to 6 months (storm damages an other environmental influences excepted)

➤ **Advantages / Special Features**

- very high colour brilliance and resolution possible
- printable on one side, no print through effect
- very light material
- fast drying time
- silky gloss surface

solvotex TCS taft plus 1

Technical Information

➤ Technical Data

➤ Carrier:

Material:	Trevira CS
Weight [g/m²]:	approx: 90
Thickness [µm]:	approx: 120 / approx: 5 mil

➤ Others:

Shelf life [years]:	2 years after the production date	
Handling/storage Conditions:	-20° to + 80°C (5° to 170 °F)	
Tear force [N/15mm] (DIN 53455):	warp / weft	151 / 93
Elongation at tear[%]:	warp / weft	49 / 64
Tear resistance [N/mm²] (DIN 53455):	warp / weft	83 / 51
flammability:	M1 (Trevira CS Standard), DIN 4102 B1, NFPA - 701	

All tests were performed in accordance with 23/50-2, DIN 50014.