

solvotex TCS 200 plus 2

Technical Information

➤ **General information**

- 100 % Trevia CS (Polyester with M1 fire classification)
- approx. 210 g/ m² incl. Inkjet coating
- light linen weave
- white
- B1 test certificate according DIN 4102-1

➤ **Areas of application**

- printable with solvent as well as with UV-curable inks
- for all kinds of application (indoor and outdoor)
- especially for displays, banners, exhibitions, presentation, graphic arts, theatre decorations etc.

➤ **Processing & Handling**

- for further handling and storage recommendations please refer to the latest product catalogue or visit our homepage under www.neschen.com
- to avoid fingerprints, protective gloves are recommended to be worn while handling
- to prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured)
- expected outdoor durability up to 6 months (storm damages and other environmental influences excepted)

➤ **Advantages / Special Features**

- highest brilliance
- fast drying time
- flat, equal surface

solvotex TCS 200 plus 2

Technical Information

➤ **Technical Data**

➤ **Carrier:**

Material:	Trevira CS
Weight [g/m²]:	approx: 210
Thickness [µm]:	approx: 320 / approx. 12,5 mil

➤ **Others:**

Shelf life [years]:	2 years after the production date	
Handling/storage Conditions:	-20° to + 80°C (5° to 170 °F)	
Tear force [N/15mm] (DIN 53455):	warp / weft	254 / 306
Elongation at tear[%]:	warp / weft	28 / 28
Tear resistance [N/mm²] (DIN 53455):	warp / weft	53 / 64
flammability:	M1 (Trevira CS Standard), DIN 4102 B1, NFPA - 701	

All tests were performed in accordance with 23/50-2, DIN 50014.