

# **solvotex TCS 300 plus 2**

## **Technical Information**

### ➤ **General information**

- 100 % Trevia CS
- approx. 330 g/ m<sup>2</sup> incl. Inkjet coating
- light linen weave
- white
- B1 test certificate according DIN 4102-1

### ➤ **Areas of application**

- printable with solvent as well as with UV-curable inks
- for all kinds of application (indoor and outdoor)
- especially for displays, banners, exhibitions, presentation, graphic arts, theatre backdrops etc.

### ➤ **Processing & Handling**

- for further handling and storage recommendations please refer to the latest product catalogue or visit our homepage under [www.neschen.com](http://www.neschen.com)
- to avoid fingerprints, protective gloves are recommended to be worn while handling
- to prevent problems after processing / laminating, make sure all prints have been allowed sufficient time to thoroughly dry (dry time of 12 hours to be assured)
- expected outdoor durability up to 6 months (storm damages and other environmental influences excepted)

### ➤ **Advantages / Special Features**

- highest brilliance
- fast drying time
- printing achieves photo quality
- flat, equal surface

# solvotex TCS 300 plus 2

## Technical Information

➤ **Technical Data**

➤ **Carrier:**

<b>Material:</b>	Trevira CS
<b>Weight [g/m<sup>2</sup>]:</b>	approx: 330
<b>Thickness [µm]:</b>	approx: 500 / approx. 19,7 mil

➤ **Others:**

<b>Shelf life [years]:</b>	2 years after the production date	
<b>Handling/storage Conditions:</b>	-20° to + 80°C (5° to 170 °F)	
<b>Tear force [N/15mm] (DIN 53455):</b>	warp / weft	692 / 254
<b>Elongation at tear[%]:</b>	warp / weft	35 / 41
<b>Tear resistance [N/mm<sup>2</sup>] (DIN 53455):</b>	warp / weft	92 / 34
<b>flammability:</b>	DIN 4102 B1, NFPA - 701	

All tests were performed in accordance with 23/50-2, DIN 50014.